



## Health, Safety and Environmental Affairs - Nitrites in Rust Inhibitors and Washing Compounds

For many years, (until 1976-77) simple, low-cost materials known as sodium nitrite ( $\text{NaNO}_2$ ) or potassium nitrite ( $\text{KNO}_2$ ) were used extensively and with great effect in metalworking fluids as ferrous rust inhibitors. This use included grinding and cutting fluids, as well as cleaners and rust inhibitors.

In October 1976 NIOSH (National Institute for Occupational Safety and Health) published a bulletin<sup>1</sup> warning that the presence of nitrosamines had been confirmed in several commercial metalworking fluids. According to that NIOSH bulletin, "...nitrosamines have been regarded as one of the most potent families of animal carcinogens..."

This bulletin set off a storm of additional research<sup>2, 3, 4, 5, 6</sup> with the end result being that all major producers of metalworking fluids, cleaners, and rust inhibitors stopped producing products containing combinations of sodium nitrite and amines. In addition, in rare cases where nitrites were still in use, most manufacturers carefully warned customers to avoid any situation where amines could be combined with nitrites in process.

As a result of all this action, and because most amines and nitrites, by themselves, are safe to use, the Federal Government (U.S.) elected not to legislate against the use of either product when used alone.

However, the use of nitrites in combination with amines in metalworking fluids is regulated by the U.S. Federal Government under 40CFR721.4740<sup>7</sup>. The language of this regulation is specific to metalworking fluids – so cleaners and rust inhibitors are not covered – even though their use and worker exposure may be similar.

Since that time, amines, particularly triethanolamine (TEA) and monoethanolamine (MEA) have remained basic building blocks of metalworking fluids, washing compounds, and rust inhibitors. Another class of amines known as "secondary amines" (primarily diethanolamine or DEA) are seldom used in these formulations in part because most secondary amines are capable of forming nitrosamines by combining with nitrogen from the atmosphere.

Alkali metal nitrites (which include sodium nitrite, potassium nitrite, and others) have largely disappeared from use in cutting and grinding fluids, but some suppliers continue to use nitrites in cleaners or rust inhibitors. Master Fluid Solutions advises that nitrite containing fluids should never be used in any

situation where amines could come into contact with them. This would include amines carried into wash or RP tanks in the form of coolant, drawing or stamping compound, or other residues carried on the parts, or any amine containing additive or treatment.

There are two primary defenses that manufacturers of nitrated cleaners or RPs use to assuage customer concerns. One is that only secondary amines (DEA or others) form nitrosamines. The other is that nitrosamines only form at low (acidic) pH. Both of these defenses have been shown to be false.<sup>8, 9</sup>

So take the advice of OSHA<sup>10</sup> and "...to minimize the potential for nitrosamine formation, nitrite-containing materials should not be added to metalworking fluids containing ethanolamines." Or, in our view, the other way around, i.e. amine containing materials should not be allowed to combine with fluids containing nitrites.

### References:

1. NIOSH "Current Intelligence Bulletin #15: Nitrosamines in Cutting Fluids" Oct. 6, 1976 <https://www.cdc.gov/mmwr/preview/mmwrhtml/0001712.htm>
2. Carcinogenicity of N-Nitrosodiethanolamine in Rats at Five Different Dose Levels. R. Preussmann et al. Institute of Toxicology and Chemotherapy, German Cancer Research Center, Heidelberg 1982
3. Persistence of N-Nitrosodiethanolamine Contamination in American Metalworking Lubricants. Keefer et al. **Chemical Toxicology** April 1990
4. OSHA HAZARD Information Bulletins N-Nitroso Compounds in Industry. March 15, 1980 [http://www.osha.gov/dts/hib/hib\\_data/hib19900315.html](http://www.osha.gov/dts/hib/hib_data/hib19900315.html)
5. Monitoring Nitrite, N-Nitrosodiethanolamine, and Mutagenicity in Cutting Fluids Used in the Metal Industry. Monarca et al. **Environmental Health Perspectives** June 1993 <http://ehp.niehs.nih.gov/members/1993/101-2/monarca-full.html>
6. N-Nitrosodiethanolamine <http://ntp.niehs.nih.gov/ntp/roc/eleventh/profiles/s126nitr.pdf>
7. Code of Federal Regulations 40CFR721.4740 <http://ecfr.gpoaccess.gov/cgi/t/text/textidx?c=ecfr&sid=ab989b6b5179359aedcd7ec435bd3811&rgn=div5&view=text&node=40:29.0.1.1.10&idno=40>
8. Reducing Nitrosamine Contamination in Cutting Fluids Loepky et al. **Food and**

## Health, Safety and Environmental Affairs - Nitrites in Rust Inhibitors and Washing Compounds

**Cosmetic Toxicology** Vol 21, No. 5 1983

9. Report to the Workers Compensation Board on the Health Effects of Occupational Exposure to Fluids Used for Machining and Lubricating in Manufacturing. Toronto, Ontario  
<http://www.canoshweb.org/odp/html/rpt18.htm>
10. Metalworking Fluids: Safety and Health Best Practices Manual OSHA [http://www.osha.gov/SLTC/metalworkingfluids/metalworkingfluids\\_manual.html](http://www.osha.gov/SLTC/metalworkingfluids/metalworkingfluids_manual.html)